

Calcined Alumina

Technical Specifications

CHEMICAL SPECIFICATION	PRODUCT CODE				
	MG 6030	MG 6520	MG 6535	MG 8010	MG 1000
P2O5	0.0012	0.0013	0.0013	0.0016	0.002
NZ2O	0.345	0.355	0.3775	0.415	0.5
FE2O3	0.043	0.03575	0.04475	0.026	0.015
SIO2	23.842	24.133	16.288	14.546	0.02
ZNO	0.00048	0.00052	0.00052	0.00064	0.0008
CAO	0.051	0.0465	0.057	0.047	0.05
TIO2	0.0624	0.0426	0.0726	0.0232	0.004
V2O5	0.0012	0.0013	0.0013	0.0016	0.002
K2O	0.0312	0.0213	0.0363	0.0116	0.002
GA2O3	0.0072	0.0078	0.0078	0.0096	0.012
MGO	0.015	0.01	0.0175	0.005	0
AL2O3 %	70	75	80	85	98.5
ALPHA %	8	9	10	10	12
LOI (300- 1000 Deg C)	1.5	2	1	1.8	1
MESH + 325	1	1	1	1	1

* Typical Values

Packing: 50 kg HDPE Bags